

ICF-11SB

MERV 11, heavy-weight 100% synthetic spunbond polyester with high-permeability.



ICF-11SB

is a high strength, 100% synthetic spunbond media with excellent durability, particulate release and moisture resistance.

| Specifications | | |
|-------------------------------|---------------------------------|--|
| Basis Weight (gram/ounces) | 260gr / 80z. | |
| Caliper | 24 mils @ 2.7 psi | |
| Air Permeability | 20 cfm/ft ² @ 0.5 wc | |
| Mullen Burst Dry | 355 psi | |
| Mullen Burst Wet | 355 psi | |
| Resin System | not applicable | |

| Test Results | |
|---------------------------------------|------|
| Airflow Rate (CFM) | 500 |
| Initial Resistance (in WG) | 0.69 |
| E1 (%) Initial Efficiency 0.30-1.0 um | 20% |
| E2 (%) Initial Efficiency 1.0-3.0 um | 70% |
| E3 (%) Initial Efficiency 3.0-10.0 um | 94% |
| MERV Rating | 11 |

| Applications |
|---------------------|
| Powder Coating |
| Pharmaceutical |
| Cement |
| Pnuematic Conveying |
| Food Processes |

Paint Pigment

8401 Air Commerce Drive, Louisville KY 40219 | toll free: 800.757.5624 | phone: 502.634.4796 | Fax: 502.969.2364 info@kochfilter.com | www.kochfilter.com