

# ICF-16AR-TX

MERV 16, 100% Spunbond polyester with laminated ePTFE membrane.



## Specifications

Basis Weight (gram/ounces)	10oz.
Air Permeability	4-7 cfm/ft <sup>2</sup> @ 0.5 wc
Mullen Burst Dry	300 psi
Mullen Burst Wet	300 psi

## Test Results

Airflow Rate (CFM)	500
Initial Resistance (in WG)	1.25
E1 (%) Initial Efficiency 0.30 -1.0 um	99.987
E2 (%) Initial Efficiency 1.0 -3.0 um	100
E3 (%) Initial Efficiency 3.0 10.0 um	100
MERV Rating	16

## Applications

Dryers
Pigments
Pharmaceutical
Plastic
Catalyst
Clinker Cooler
Metal Kiln

8401 Air Commerce Drive, Louisville KY 40219 | toll free: 800.757.5624 | phone: 502.634.4796 | Fax: 502.969.2364  
[info@kochfilter.com](mailto:info@kochfilter.com) | [www.kochfilter.com](http://www.kochfilter.com)